





Rolland Enviro® Print is an uncoated paper that must be processed like any other paper in this category.

COMPLIANCE WITH THE FOLLOWING PARAMETERS WILL ENSURE OPTIMAL PRINTING ON THIS PAPER.



PRIOR TO PRINTING

Flip 50 sheets to verify the print quality on both sides of the paper.

PRE-PRESS AND SCREEN RULING

Use GCR mode (Gray Component Replacement). Screen ruling should be between 150 lpi and 175 lpi.

INKS

Total ink accumulation must not exceed 260% for a rotary press, and 300% for a sheet-fed press. Use ink with a tack value between 12 and 10. Ink density should be set a \pm .05 black 135, cyan 115, magenta 120, yellow 100. Damping solution pH should be over 4.5.

DRYING

Standard drying time for uncoated paper between 20 and 40 minutes, depending on the ink coverage.











Customer service: 1 800 567-9872

rollandinc.com

